

Typical analysis: NiV 93:7 wt%

Material	Purity		
NiV 93:7 wt%			
Element	Impurity [wt%]		
Si	0,02		
Fe	0,03		
C	0,025		
N	0,005		
O	0,035		